

IN THE CLAIMS:

Please amend the claims as follows:

3. (Amended) The laminate according to claim 1, wherein said tetrafluoroethylene copolymer comprises 40 to 81 % by mole of tetrafluoroethylene and 60 to 19 % by mole of other monomer.

4. (Amended) The laminate according to claim 1, wherein said tetrafluoroethylene copolymer has a melt flow rate of 1.0 to 100 g/10 minutes.

5. (Amended) The laminate according to claim 1, wherein said tetrafluoroethylene copolymer has a melt flow rate of 1.0 to 50 g/10 minutes.

6. (Amended) The laminate according to claim 1, wherein said tetrafluoroethylene copolymer has a critical shear rate of 10 to 10^3 sec^{-1} at 230°C.

7. (Amended) The laminate according to claim 1, wherein said tetrafluoroethylene copolymer comprises tetrafluoroethylene, ethylene, a fluorovinyl compound of the formula (I):



wherein Rf is a fluoroalkyl group having 2 to 10 carbon atoms, and hexafluoropropylene, in which a molar ratio of

[illegible]
$$X \times Y/100 \geq 10.0.$$

10. (Amended) A tubular member comprising a laminate according to claim 1.

 a^3

ad

15. (Amended) A sheet comprising a laminate according to claim 1.